


7040 Real Red



7041 Primary



7042 Wasabi



7043 Sandy



7030 Jasper



7044 Desert Night




7005 Bright Blue



7045 Suede



7013 Peacock



7036 Mist



7029 Cypress



7012 Burgundy



7034 Douglas Fur



7001 Periwinkle



7033 Azure



7047 Calcine Grey



7048 Royal



7018 Navy



7020 Black

Staccato grade two

Made with 100% Cordura Nylon

Specifications

Weaving	Fancy
Contents	100% Cordura Nylon
Weight/linear yard	Ounces: 17 ± 1
Width	Inches usable: 54

Performance

Breaking strength (Grab Test) ASTM D-5034	Warp: 350 lbs (min.) Fill: 280 lbs (min.)
Colour fastness to light AATCC-16 (40 hours)	L5
Colour fastness to crocking AATCC-8	Dry: Class 4 min. Wet: Class 4 min.
Abrasion resistance (#10 cotton duck) ASTM D-4157 Mod.	Warp: 1 900 000 Double rubs Fill: 1 500 000 Double rubs
Seam Slippage ASTM D-434	Warp: 45 lbs (min.) Fill: 45 lbs (min.)
Bursting strength ASTM D-3787 Taber	330 cycles min.
Stain resistance	PASSED
Water repellency AATCC-22 (80-ISO 3)	
Soil resistance oil repellency AATCC-118 (Grade 7)	PASSED
Cleaning code	WS
Flammability	
State of California Technical bulletin 117 Section E (CS-191-53)	PASSED
UFAC	Class 1

The modified Wyzenbeek (Abrasion resistance) test was developed by Dupont. Comparative test results indicated that approximately 600 Double Rubs cycles on the modified Wyzenbeek are equal to 1,000,000 Double Rubs cycles on the standard ASTM D-3597 SEC. 7.4 Wyzenbeek test.

Dye lots may vary slightly from samples shown.